

TECHNICAL DATA SHEET
YIPIN[®] Anticorrosion Pigment
Mica iron oxide gray MIOG-2



Edition of	2012-02-16
Type	Pigment Similar Grey
Delivery Form	Powder
Chemical Class	Mica Iron Oxide Grey α -Fe ₂ O ₃
Color Index	Pigment Grey 11 (77499)
CAS No.	1309-37-1
Use Recommendation	Coating

TECHNICAL DATA

	<u>Min</u>	<u>Max</u>	<u>Test Method</u>
Water-Soluble Content [%]		0.3	DIN ISO787 Part 3
Sieve Residue (0.045mm) [%]		5.0	DIN 53195
PH Value	5.5	7.5	DIN ISO787 Part 9
Fe ₂ O ₃ [%]	90.0		HG-T 3006
Moisture (After Production) [%]		1.0	DIN ISO 787 Part 2
Flake Content[%]	60		DIN ISO 10601

	<u>Approx.</u>	
Oil Absorption [g/100g]	~15	DIN ISO787 Part 5
Tamped Density [g/ml]	2.2~2.6	DIN ISO 787 Part 11
Density [g/ml]	~4.9	DIN ISO 787 Part 10

STANDARD PACKAGING 25kg/bag

TRANSPORT AND STORAGE

Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature. Special conditions for opened packaging: Close bags after use to prevent the absorption of moisture and contamination.

SAFETY

The product is not classified as dangerous under the relevant EC directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations. In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labeling and transport of dangerous substances must be ensured.

The information contained in the safety data sheet should be observed.

This contains information on handling, product safety and ecology.

YIPIN PIGMENTS, INC. Tel:+1-909-243-7394 Fax: +1-909-243-7397 www.yipin.com
一品颜料 Tel:+86-21-5950 8509 Fax: +86-21-5950 7893 wh@yipin.com

TECHNICAL DATA SHEET
YIPIN[®] Anticorrosion Pigment
Mica iron oxide gray MIOG-2



This information is given in good faith, without warranty. It is also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General conditions of sale and delivery.