TECHNICAL DATA SHEET

YIPIN[®] Pearl Luster Pigment Platinum pearl Y9205



Edition of	2012-02-16
Туре	Rainbow Series

Delivery Form Powder

 Chemical Class
 $Ti0_{2(x)}/[KA1_2(A1Si_3O_{10}) (OH)_2]$

 CAS No.
 12001-26-2、13463-67-7

Use RecommendationCoating/ Plastics/ Paper/ Print ect.

TECHNICAL DATA			
			Test Method
Particle Size [um]		10~60	Optical Microscope
Particle Diameter Distributio	n [%] ≥		
(Particle proportion within	nominal	92	Laser Particle Size Analyzer
grain diameter range)			
Water-Soluble Content [%]	≤	0.3	DIN ISO787 Part 3
Water Content [%]	\leq	0.5	DIN ISO787 Part 2
PH Value		6~9	DIN ISO787 Part 9
Thermal Stability [℃]	≤	800	
Particle Shape		Flake	Electronic Microscope
TiO ₂ Type		Rutile	
Luster		Bright	
Color (reflection)		Gold	
(transmission)		Baby blue	
		Approx.	
Bulk Density [g/100ml]		28~32	DIN 53466
Density [g/ml]		3.1~3.2	DIN ISO787 Part 11
Oil Absorption[g/100g]		45~55	DIN ISO787 Part 5
Content [%] Mica		44~48	
TiO ₂		52~56	
SnO ₂		<1	

STANDARD PACKAGING	3kg/bag 25kg/drum	
--------------------	-------------------	--

TRANSPORT AND STORAGE

Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature. Special conditions for opened packaging: Close bags after use to prevent the absorption of moisture and contamination.

TECHNICAL DATA SHEET

YIPIN[®] Pearl Luster Pigment Platinum pearl Y9205



SAFETY

The product is not classified as dangerous under the relevant EC directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations. In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labeling and transport of dangerous substances must be ensured.

The information contained in the safety data sheet should be observed.

This contains information on handing, product safety and ecology.

This information is given in good faith, without warranty. It is also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General conditions of sale and delivery