

TECHNICAL DATA SHEET
YIPIN® Pearl Luster Pigment
Blackish green Y9408



Edition of	2012-02-16
Type	Colour & pigmentation Series
Delivery Form	Powder
Chemical Class	TiO _{2(x)} /[KAl ₂ (AlSi ₃ O ₁₀)(OH) ₂]
CAS No.	12001-26-2、13463-67-7
Use Recommendation	Coating/ Plastics/ Paper/ Print ect.

TECHNICAL DATA

		<u>Test Method</u>
Particle Size [um]	10~60	Optical Microscope
Particle Diameter Distribution [%] ≥ (Particle proportion within nominal grain diameter range)	92	Laser Particle Size Analyzer
Water-Soluble Content [%] ≤	0.3	DIN ISO787 Part 3
Water Content [%] ≤	0.5	DIN ISO787 Part 2
PH Value	6~9	DIN ISO787 Part 9
Thermal Stability [°C] ≤	180	
Particle Shape	Flake	Electronic Microscope
TiO ₂ Type	Anatase	
Luster	Bright	
Color (reflection)	Silver	
(transmission)	Blackish green	
Approx.		
Bulk Density [g/100ml]	22~26	DIN 53466
Density [g/ml]	3.0~3.1	DIN ISO787 Part 11
Oil Absorption[g/100g]	60~70	DIN ISO787 Part 5
Content [%] Mica	50~55	
TiO ₂	44~49	
SnO ₂	-	
Absorptive pigment	<1	

STANDARD PACKAGING	3kg/bag	25kg/drum
---------------------------	---------	-----------

TRANSPORT AND STORAGE

Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature. Special conditions for opened packaging: Close bags after use to prevent the absorption of moisture and contamination.

YIPIN PIGMENTS, INC. Tel:+1-909-243-7394 Fax: +1-909-243-7397 www.yipin.com
 一品颜料 Tel:+86-21-3950 0127 Fax: +86-21-5950 7893 gwq@yipin.com

TECHNICAL DATA SHEET
YIPIN[®] Pearl Luster Pigment
Blackish green Y9408



SAFETY

The product is not classified as dangerous under the relevant EC directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations. In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labeling and transport of dangerous substances must be ensured.

The information contained in the safety data sheet should be observed.

This contains information on handling, product safety and ecology.

This information is given in good faith, without warranty. It is also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General conditions of sale and delivery